

BRUSH-N-SEAL WATERPROOFING

PRODUCT SPECIFICATIONS

COMPOSITION: Liquid applied, polymer emulsion

COLOR: Green or Grey

SOLIDS: 55% by weight

THICKNESS: 1.52 mm (60 mils wet), 1 mm (40 mils dry)

MINIMUM TEMP FOR APPLICATION: 4°C (40 °F)

APPLICATION: Brush/Trowel/Airless spray

APPLICATION RATE: 2.31-2.80 sq m/3.79 L (25-30 sq ft/gal)

PROPERTY	TEST METHOD	RESULTS
Elongation	ASTM D412	1,135%
Low Temp Flex	Bend around 1" mandrel	-33 C (-27 F)
Crack Bridging Ability	ASTM C836	-32 C (-26 F)
Tensile Strength	ASTM D412	2068 kPa (300 psi)
Adhesion to Concrete	ASTM C836	4.2 lbs.